



Technical data sheet

Rapidweiss

Product description

Characteristics:

- Single coating paint with very good hiding power
- Keeps structure
- For interior use
- Dull mat
- High efficiency
- Fast and homogeneous colour spreading
- Excellent application characteristics
- Fine structure
- This product complies with the requirements of the Blue Angel for low-emission interior paints RAL-UZ 102 * (Ecolabel of the federal government to protect human health and the environment)
Blue Angel is only valid for Rapidweiss White

* Test certificate available upon request.

DIN EN 13300:

- Wet scrub resistance: class 2
- Contrast ratio: hiding power class 1 (≥ 99.5) at a spreading rate of 125 ml/m²
- Gloss level: dull mat
- Maximum particle (grit) size: fine (< 100 μm)

Material

Application Area:

For interior use, on new and old solid old undergrounds, such as stucco, concrete, woodchip wallpaper, gypsum board (without lignin marks).

Binding Agent:

Vinyl-acetate dispersion

Colour:

White / Mix2 / Mix3

Content of Solids:

Approx. 55.5 %

Specific gravity:

1.48 g/cm³

pH value:

Approx. 10

Diluting agent:

Water

Viscosity:

Slightly thixotropic



Technical data sheet

JONAS Rapidweiss

Application Characteristics

Application:	Brush / roller / spray (airless).
Underground:	Needs to be clean, dry, and solid. Otherwise use JONAS Acryl-Tiefgrund or JONAS Hydro PowerGrip Gel first to consolidate the underground. For underground treatment and application VOB, part C, DIN 18363 and the relevant BFS information must be observed.
Coating build-up:	Priming coat: No dilution or dilute product with a maximum of 5% water. Final coating: use product without dilution.
Spreading rate per coating:	Approx. 150 ml/m ² on smooth underground (if necessary test on the wall).
Application temperature:	At least + 5°C (Degrees Celsius) for air and underground during application and drying.
Drying:	The surface of the coating is dry and can be painted over after 8 - 10 hours (at a temperature of 20 °C and a relative atmospheric humidity of 65 %).
Tinting:	Product can be tinted with JONAS Allcolor Vollton- und Abtönfarben. Tinting may lead to variations in the technical data.
Cleaning of tools:	Clean with water immediately after use.

General information

Storage:	Cool, but not freezing.
Shelf-life:	Can be stored for at least 12 months after date of filling (see additional sticker) if stored properly in the unopened original packaging.
Art.No. and description:	00 70 507-01 JONAS Rapidweiss White 00 70 307-01 JONAS Rapidweiss Mix2 00 70 407-01 JONAS Rapidweiss Mix3
Packaging:	White: 5 l Mix2: 5 l Mix3: 4.75 l
Ingredients acc. to VdL RL01:	Vinyl-acetate dispersion, white pigment, calcium carbonate, silicate, water, additives, preservative, BIT/MIT/zinc pyrithione.
Safety:	Please follow the instructions of the safety data sheet.
Labelling:	This product is not classified according to EU regulation No 1272/2008 [CLP].
Product-code:	BSW20
VOC content:	EU-Limit for the product Kat. A/a: 30 g/l (2010). This product contains < 1 g/l VOC.
Waste disposal:	Empty containers can be disposed for recycling. Any dried residues of material can be disposed of as construction waste or together with domestic garbage. Containers with liquid material residues must be disposed of according to local regulations. For further information, please contact your local waste authority.
Advice acc. to CLP:	Keep out of reach of children. Warning! Hazardous respirable droplets may be formed when sprayed. Do not breathe spray or mist. Wear appropriate respiratory protection (full mask / half mask equipped with filter type A2/P2). Avoid eating, drinking and smoking during use of the product. Ensure good ventilation during and after application. In case of contact with eyes or skin, rinse immediately with plenty of water. Do not empty into drains or water courses. Contains: 1,2-Benzisothiazol-3(2H)-on / 2-Methyl-2H-isothiazol-3-on / zinc pyrithione. May produce an allergic reaction. Safety data sheet available on request. Advice for people suffering from isothiazolinone allergy under phone-no.: +49(0)2058/789-0.